

SPECIFICATION

OXIDIZED BITUMEN 10/20



	SPECIFICATION	TEST METHOD
Specific gravity @ 25/25 °C	1.00-1.06	D-70
Penetration@25°C	10-20	D-5
Softening point °C	90 min	D-36
Ductility@25°C	2	D-113
Loss on heating (wt)%	0.5	D-6
Flash point °C	230 min	D-92
Solubility in CS ₂ (wt)%	99 min	D-4

PRODUCT CAPACITY: 5,000 MT per Month

PAKING:

- Carton Box (20 Kg) (25 Kg)
- Polyamide Bags (20 Kg) (25 Kg)
- Kraft Bags (20 Kg) (25 Kg)
- Drums (20 Kg) (25 Kg) (150 Kg) (185 Kg)



PETRO TAR KIMIYA CO. (PETRO TAR CO.)

REFINERY: No.3943 , Sousan 2 St, Molasadra Blv., Aboureyhan Blv.,
Eshtehard Industrial Park, Alborz, IRAN
Tel: (+98263) 7776830-3 Fax: (+98263) 7776834
WWW.PETROTARCO.COM