

SPECIFICATION

BITUMEN 20/30



	SPECIFICATION	TEST METHOD
Specific gravity @25/25 °C	1.01-1.06	D-70
Penetration @25 °C	20-30	D-5
Softening point °C	55-63	D-36
Ductility @25 °C	100 min	D-113
Loss on heating (wt)%	0.2 max	D-6
Drop in penetration after heating %	20 max	D-6 & D-5
Flash point °C	230 min	D-92
Solubility in CS ₂ (wt)%	99.5 min	D-4
Spot test	negative	*A.A.S.H.O.T.102

PRODUCT CAPACITY: 10,000 MT per Month

PAKING: New Steel Drums (150 Kg) (185 Kg)

CAPACITY OF 20' CONTAINER: 110 Drum



PETRO TAR KIMIA CO. (PETRO TAR CO.)

REFINERY: No.3943 , Sousan 2 St, Molasadra Blv., Aboureyhan Blv.,
Eshtehard Industrial Park, Alborz, IRAN
Tel: (+98263) 7776830-3 Fax: (+98263) 7776834
WWW.PETROTARCO.COM