

SPECIFICATION

BITUMEN 40/50



| | SPECIFICATION | TEST METHOD |
|-------------------------------------|---------------|------------------|
| Specific gravity @ 25/25 °C | 1.01-1.06 | D-70 |
| Penetration @ 25 °C | 40-50 | D-5 |
| Softening point °C | 52-60 | D-36 |
| Ductility@ 25 °C | 100 min | D-113 |
| Loss on heating (wt)% | 0.2 max | D-6 |
| Drop in penetration after heating % | 20 max | D-6 & D-5 |
| Flash point °C | 230 min | D-92 |
| Solubility in CS ₂ (wt)% | 99.5 min | D-4 |
| Spot test | negative | *A.A.S.H.O.T.102 |

PRODUCT CAPACITY: 10,000 MT per Month

PAKING: New Steel Drums (150 Kg) (185 Kg)

CAPACITY OF 20' CONTAINER: 110 Drum



PETRO TAR KIMIA CO. (PETRO TAR CO.)

REFINERY: No.3943 , Sousan 2 St, Molasadra Blv., Aboureyhan Blv.,
Eshtehard Industrial Park, Alborz, IRAN
Tel: (+98263) 7776830-3 Fax: (+98263) 7776834
WWW.PETROTARCO.COM