

# SPECIFICATION

## BITUMEN 80/100



	SPECIFICATION	TEST METHOD
Specific gravity @25/25 °C	1.01-1.05	D-70
Penetration @ 25 °C	80-100	D-5
Softening point °C	45-52	D-36
Ductility @ 25 °C	100 min	D-113
Loss on heating (wt)%	0.5 max	D-6
Drop in penetration after heating %	20 max	D-6 & D-5
Flash point °C	230 min	D-92
Solubility in CS <sub>2</sub> (wt)%	99.5 min	D-4
Organic matter insoluble in CS <sub>2</sub> (wt)%	0.2 max	D-4
Spot test	negative	*A.A.S.H.O.T.102

**PRODUCT CAPACITY:** 10,000 MT per Month

**PAKING:** New Steel Drums (150 Kg) (185 Kg)

**CAPACITY OF 20' CONTAINER:** 110 Drum



**PETRO TAR KIMIA CO. (PETRO TAR CO.)**

**REFINERY:** No.3943, Sousan 2 St, Molasadra Blv., Aboureyhan Blv.,  
Eshtehard Industrial Park, Alborz, IRAN  
Tel: (+98263) 7776830-3 Fax: (+98263) 7776834  
WWW.PETROTARCO.COM