

# SPECIFICATION

## OXIDIZED BITUMEN 85/25



	SPECIFICATION	TEST METHOD
Specific gravity@25/25 °C	1.05 approx	D-70
Penetration@25°C	20-30	D-5
Softening point °C	80-90	D-36
Ductility@25°C	1.5 min	D-113
Loss on heating (wt)%	0.2 max	D-6
Flash point °C	230 min	D-92
Solubility in CS2 (wt)%	99 min	D-4

**PRODUCT CAPACITY:** 5,000 MT per Month

### PAKING:

- Carton Box (20 Kg) (25 Kg)
  - Polyamide Bags (20 Kg) (25 Kg)
  - Kraft Bags (20 Kg) (25 Kg)
  - Blocks (20 Kg)\_ (25 Kg) (40 Kg)
  - Drums (20 Kg) (25 Kg) (150 Kg) (185 Kg)
- Other Packings and weights are welcome from Clients



### PETRO TAR KIMIA CO. (PETRO TAR CO.)

**REFINERY:** No.3943 , Sousan 2 St, Molasadra Blv., Aboureyhan Blv.,  
Eshtehard Industrial Park, Alborz, IRAN  
Tel: (+98263) 7776830-3 Fax: (+98263) 7776834  
WWW.PETROTARCO.COM