

SPECIFICATION

OXIDIZED BITUMEN 90/10



	SPECIFICATION	TEST METHOD
Specific gravity @25/25 °C	1.05 approx.	D-70
Penetration @25°C	5-15	D-5
Softening point °C	85-95	D-36
Ductility@25 °C	1.5 min	D-113
Loss on heating (wt)%	0.2 max	D-6
Flash point °C	230 min	D-92
Solubility in CS2 (wt)%	99 min	D-4

PRODUCT CAPACITY: 5,000 MT per Month

PACKING:

- Carton Box (20 Kg) (25 Kg)
 - Polyamide Bags (20 Kg) (25 Kg)
 - Kraft Bags (20 Kg) (25 Kg)
 - Blocks (20Kg) (25 Kg) (40 Kg)
 - Drums (20 Kg) (25 Kg) (150 Kg) (185 Kg)
- Other Packings and weights are welcome from Clients



PETRO TAR KIMIA CO. (PETRO TAR CO.)

REFINERY: No.3943 , Sousan 2 St, Molasadra Blv., Aboureyhan Blv.,
Eshtehard Industrial Town, Alborz, IRAN
Tel: (+98263) 7776830-3 Fax: (+98263) 7776834
WWW.PETROTARCO.COM